



Die Attach Adhesives

DIE ATTACH FILM

Product Name	Description	Key Attributes	Glass Transition Temperature, T _g (°C)	Viscosity at 25°C	Coefficient of Thermal Expansion, CTE (ppm/°C)		Modulus at 25°C (MPa)	Recommended Cure
					Below T _g	Above T _g		
Non-Conductive								
LOCTITE ABLESTIK ABP 2035SCR	Silica-filled die attach adhesive	• One component • Low stress • Snap cure or low temperature oven cure • Excellent dispensing performance for high throughput applications • Compatible with dam and fill encapsulants	118	9,830 at 5 rpm	50	135	1,500	2 min. at 120°C
LOCTITE ABLESTIK ABP 2024	BMI hybrid die attach adhesive	• Low outgassing • One component • High reliability	47	13,000 at 5 rpm	127	156	510	30 min. ramp + 30 min. hold at 175°C
LOCTITE ABLESTIK ABP 2040 LV	Epoxy non-conductive die attach adhesive	• One component • Fast cure • Low temperature cure • Low stress • Low warpage	28	11,000 at 5 rpm	39	129	2,603	2 min. at 120°C
LOCTITE ABLESTIK GA 2W	Acrylic die attach adhesive	• Very low stress • Low chip warpage • Improved viscosity • Thixotropic • Good dispensability • One component	25	10,000 at 5 rpm	58	164	70	30 min. ramp + 15 min. hold at 175°C

Henkel AG & Co. KGaA
Henkelstraße 67
40589 Düsseldorf | Germany

Phone: +1 952 486 6313
E-mail: electronics@henkel.com
www.henkel-adhesives.com/electronics



The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention. The information is protected by copyright. In particular, any reproductions, adaptations, translations, storage and processing in other media, including storage or processing by electronic means, enjoy copyright protection. Any exploitation in whole or in part thereof shall require the prior written consent of Henkel AG & Co. KGaA. Except as otherwise noted, all marks used in this document are trademarks and/or registered trademarks of Henkel and/or its affiliates in the US, Germany, and elsewhere. © Henkel AG & Co. KGaA, 02/2018



Die Attach Adhesives

DIE ATTACH PASTE

Product Name	Description	Key Attributes	Glass Transition Temperature, T _g (°C)	Viscosity at 25°C	Coefficient of Thermal Expansion, CTE (ppm/°C)		Modulus at 25°C (MPa)	Recommended Cure
					Below T _g	Above T _g		
Non-Conductive								
LOCTITE ABLESTIK ABP 2035SCR	Silica-filled die attach adhesive	• One component • Low stress • Snap cure or low temperature oven cure • Excellent dispensing performance for high throughput applications • Compatible with dam and fill encapsulants	118	9,830 at 5 rpm	50	135	1,500	2 min. at 120°C
LOCTITE ABLESTIK ABP 2024	BMI hybrid die attach adhesive	• Low outgassing • One component • High reliability	47	13,000 at 5 rpm	127	156	510	30 min. ramp + 30 min. hold at 175°C
LOCTITE ABLESTIK ABP 2040 LV	Epoxy non-conductive die attach adhesive	• One component • Fast cure • Low temperature cure • Low stress • Low warpage	28	11,000 at 5 rpm	39	129	2,603	2 min. at 120°C
LOCTITE ABLESTIK GA 2W	Acrylic die attach adhesive	• Very low stress • Low chip warpage • Improved viscosity • Thixotropic • Good dispensability • One component	25	10,000 at 5 rpm	58	164	70	30 min. ramp + 15 min. hold at 175°C

Henkel AG & Co. KGaA
Henkelstraße 67
40589 Düsseldorf | Germany

Phone: +1 952 486 6313
E-mail: electronics@henkel.com
www.henkel-adhesives.com/electronics



The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention. The information is protected by copyright. In particular, any reproductions, adaptations, translations, storage and processing in other media, including storage or processing by electronic means, enjoy copyright protection. Any exploitation in whole or in part thereof shall require the prior written consent of Henkel AG & Co. KGaA. Except as otherwise noted, all marks used in this document are trademarks and/or registered trademarks of Henkel and/or its affiliates in the US, Germany, and elsewhere. © Henkel AG & Co. KGaA, 02/2018